

# **Product Data Sheet Eastman Cellulose Acetate Butyrate (CAB-551-0.2)**

## Application/Uses

- Automotive OEM
- Coatings for Automotive Plastics
- Coatings for automotive
- Coatings for plastic
- Coatings
- Nail care
- Truck/Bus/Commercial Vehicles

## **Product Description**

Eastman Cellulose Acetate Butyrate (CAB-551-0.2) is a cellulose ester with high butyryl content and relatively low molecular weight. It is compatible with numerous cross-linking resins and has a lower solution viscosity. In coatings, Eastman CAB-551-0.2 gives clear films, reduces surface tack and mottling, minimizes cratering, improves flow and thermal reflow, and provides intercoat adhesion and good UV stability. It is useful for durable cross-linked formulations. Its good compatibility with a wide range of curing resin systems and its solubility in a wide variety of solvents and solvent combinations make it useful as an additive in numerous coating compositions.

#### **Typical Properties**

Butyryl Content	52 wt %
Acetyl Content	2 wt %
Hydroxyl Content	1.8%
Viscosity <sup>a</sup>	0.76 poise
Color b	50 ppm
Haze <sup>b</sup>	15 ppm
Acidity as Acetic Acid	0.02 wt %
Ash Content	<0.05%
Refractive Index	1.475
Melting Point	130-140°C
Glass Transition Temperature (T <sub>q</sub> )	101°C
Specific Gravity	1.16
Wt/Vol	1.16 kg/L (9.67 lb/gal)
Bulk Density	
Poured	515 kg/m $^{3}$ (32 lb/ft $^{3}$ )
Tapped	612 kg/m $^{3}$ (38 lb/ft $^{3}$ )
Dielectric Strength	787-984 kv/cm (2- 2.5 kv/mil)
Molecular Weight <sup>c</sup> M <sub>n</sub>	30000
Tukon Hardness	15 Knoops

#### **Comments**

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.